



GETAHINDUS (M) SDN BHD (49583-A)

H.Q : No. 20 & 22, Jalan Selat Selatan 6, Off Jalan Banting, Landpac Industrial Park,
42000 Port Klang, Selangor Darul Ehsan, Malaysia.
Tel: 03-31683333 Fax: 03-31683399 E-Mail: gimsb@tm.net.my Website: http://www.getahindus.com.my
Factory : Lot 809, Batu 13 1/2, Jalan Muar, 84900 Tangkak, Johor Darul Takzim, Malaysia.
Tel: 06-9791188 Fax: 06-9784617 E-mail: gimsbft@tm.net.my



GICOM MBR

GICOM MBR

M07/R3/S0606

GICOM MBR is a pre-vulcanised natural rubber latex preserved with ammonia. It provides high clarity and medium modulus properties to dipped products. It also gives excellent casting, good ageing properties and good binding characteristic to other products.

GICOM MBR can be used in many variety of dipping applications, casting, binding, etc.; particularly suitable for manufacturing rubber mould and toys.

1. TYPICAL PROPERTIES

Total Solid Content (%)	-	58.0 ± 0.5
Alkalinity (%)	-	0.60 min.
MST @ 55% TSC (sec.)	-	900 min.
B/F Viscosity, 2/60 at 26±2 °C (cps)	-	1200 – 1500
pH	-	10.50 ± 0.5

2. TYPICAL DIPPED FILM PROPERTIES OF **GICOM MBR**

(TYPICAL EXAMINATION GLOVES FILM WITH THICKNESS 0.12 – 0.15mm TESTED IN ACCORDANCE WITH ASTM)

UNAGED (ASTMD412:1992)

Modulus at 700% Elongation (MPa)	11.0 – 15.0
Tensile Strength (MPa)	24.0 – 29.0
Elongation at Break (%)	800 - 950

AGED (22hrs at 100°C)–(ASTMD573:1988)

Modulus at 700% Elongation (MPa)	8.0 min.
Tensile Strength (MPa)	19.0 min.
Elongation at Break (%)	800 min.

3. APPLICATION

GICOM MBR is suitable for all categories of casting, binding and dipping especially for rubber mould, toys etc..

4. PACKING

GICOM MBR is packed in non-returnable metal drums of net weight 205kg or delivered in bulk tank.

The above information is given in good faith and without liability.

5. STORAGE

It is recommended to store this product under shade without exposure to direct sunlight at temperature below 35°C but not in freezing conditions. This will prevent the product from creaming and if this happens, stirring is required to re-disperse the cream.

A properly stored product should have a shelf life of 6–12 months. Longer storage than this period is not recommended.

6. TECHNICAL SERVICE AND INFORMATION

The GETAHINDUS TECHNICAL TEAM comprises of qualified and experienced personnel. All R & D works are carefully thought of and meticulously planned when developing new products and materials to suit customers' requirements. All technical information and samples for evaluation are readily available. For any enquiry, please contact our Sales & Marketing Department.

7. HEALTH HAZARD AND SAFETY

GICOM MBR is an ammoniated latex compound containing vulcanizing ingredients. It is not to be consumed. No adverse physiological reactions have been observed when handling the product correctly and using it in the way suggested.

Avoid direct contact with the skin and eyes. If latex is accidentally splashed onto the eyes, wash with plenty of running water and consult a medical doctor immediately.

Presented by Distributor:**Helmut Bergk GmbH**

Röderbergweg 41

D 60314 Frankfurt am Main

Phone: +49-69-499930

Fax: +49-69-94414458

E Mail: Bergk.GmbH@t-online.de