

Delivery Program

Synthetic Rubber

Polyisoprene Rubber (IR)

SKI-3

(Origin: Russia)

SKI-3-S

(Origin: Russia)

Butylrubber (IIR)

BK1675N

(Origin: Russia)

Styrene-Butadiene-Rubber

SBR 1500 / 1502 / 1507 / 1712

(Origin: Russia and others)

Polybutadiene Rubber (BR)

available upon request, (TiBr, Origin: Russia)

EPDM Rubber

available upon request, (Origin: Russia)

Product Details:

Types	SKI-3	SKI-3-S	BK1675N	SBR 1500	SBR 1502	SBR 1507 ¹⁾ SBR 1508 ²⁾	SBR 1712
Cis content %	97,5	97,5					
Unsaturation %			1,6 +/-0,2				
Mooney Viscosity	80 +/-5 70 +/-5	80 +/- 8	52 +/- 5 50 +/- 5	52 +/- 6 50 +/- 5	53 +/- 5 50 +/- 5	39 +/- 3 ¹⁾ 50 +/- 4 ²⁾	53 +/- 5 50 +/- 5
Styrene content %				23,5+/-1,5	23,5+/-1,5	23,5+/-1,5	23,5+/-1,5
Oil content %							27,5+/-1,5
Antioxidant, - staining - non staining	x			x			x

The above mentioned rubbers are of high quality standard and constantly used in all Europe and abroad for the production of tires and technical rubber goods.

Packing: 30 kg bales, PE- wrapped, in wooden boxes of 450 kg net / 500-510 kg gross,
 20 ft container holding 9,9 tons net, 40 ft container holding max 21,6 tons net

For further product information and Material Safety Data Sheets please contact us direct.

LiePro SK E 0904

The above data have been compiled to the best of our knowledge on the basis of detailed tests and represent the level of many years of practical experience of producers. No claims of liability or guarantee may be brought against us either from or in connection with this data sheet. Reprinting, even in part, only with our consent.